



# 产品承认书

## SPECIFICATION FOR APPROVAL

客户名称:  
CUSTOMER

我司料号: XRTC404030S100MBCA  
OUR PART NO.

我司品名: Miniaturized integrated inductor  
OUR PART NAME

送样日期: 数量: 0PCS  
DATE SAMPLES QUANTITY

<b>制造确认 MANUFACTURER APPROVE</b>		
拟制 DRAWN	审核 CHECKED	确认 APPROVED
Liu Jialing	Rao ping	Li Zhengxiong

<b>客户确认 CUSTOMER APPROVE</b>	
客户名称 CUSTOMER NAME:	
客户料号 CUSTOMER P/N:	
规格型号 DESCRIPTION:	measure 404030 Inductance: 10uH
检查结果: <input type="checkbox"/> 合格 <input type="checkbox"/> 不合格	签名及盖章:
INSPECT RESULT ACCEPT REJECT	SIGNATURE AND STAMP
说明 REMARK:	

如对本承认书内容有异议请提出或标记发送至我司，本承认书在未收到异议回复时于本承认书提供一周后生效。

If you have any objection to the contents of this acknowledgement, please put forward or mark it and send it to our company. This acknowledgement will take effect one week after it is provided if you do not receive an objection reply.

东莞市祥如电子有限公司  
Dongguan xiangru electronics co., ltd

Tel: 0769-86346548 Fax: 0769-86346358

e-mail: dgxiangru@126.com

## 1. Scope

### Features

- 11 Metal material for large current and low loss.
- 12 High performance (Isat) realized by metal dust core.
- 13 Low loss realized with low Rdc.
- 14 Closed magnetic circuit design reduces leakage flux.
- 15 Vinyl thermal spray, better surface compactness.
- 16 Environmental requirements must comply with the QESP-44 document
- 17 100% lead (Pb) free meet RoHS2.0 and Halogen , Reach and other legal and regulatory requirements standard.

### Application

- 2.1 DC/DC converters.
- 2.2 Pad,Smart phone.
- 2.3 Portable gaming devices, Smart wear, Wi-Fi module.
- 2.4 Notebooks, VR, AR.
- 2.5 LCD displays, HDDs, DVCs, DSCs, etc.
- 2.6 Baseband power supply, Amplifier, Power management, Module power supply, Camera power manageme.

## 2. Ordering Procedure

**XRTC 4040 30 S 100 M B C A**  
**① ② ③ ④ ⑤ ⑥ ⑦ ⑧ ⑨**

①Series Name: Mini Molding Power Inductors

②External Dimensions(L×W):4040=4.0\*4.0 mm

③External Dimensions(H):30=3.0 mm

④Size Tolerance:S=±0.2mm

⑤Inductance value:100=10uH

⑥Tolerance:M=±20%

⑦Coating color:B =Black

⑧Product type:C=Common


⑨Special define:A=Routine

For special characteristics, please refer to the specific values in Item 5 "Specifications".


---

### 3. SHAPE AND DIMENSIONS

Outline Dimensions



Recommend Land Pattern Dimensions



Units:mm

Series	L	G	W	E	T	A	B	C
XRTC404030S	4.1±0.2	1.3±0.2	4.1±0.2	1.40±0.2	3.00Max.	4.10	1.10	4.10

### 4. Marking

No Marking

### 5. Specifications

P/N	L0(μH) @ (0A) 1MHz	Rdc(mΩ)		Heat rating current Irms(A)		Saturation current Isat(A)	
		Typical	Max	Typical	Max	Typical	Max
XRTC404030S100MBCA	10.0	92	110	3.7	3.3	4.9	4.5

#### Test remarks

Note 1.: All test data is referenced to 25 °C ambient.

Note 2.: Test Condition:1MHz, 1.0Vrms.

Note 3.: Irms:DC current (A) that will cause an approximate ΔT of 40 °C.


Note 4.: Isat:DC current (A) that will cause L0 to drop approximately 30%.

Note 5.: Operating Temperature Range -55°C to +125°C.

Note 6.: The part temperature (ambient + temp rise) should not exceed 125 under °C the worst case operating conditions. Circuit design, component placement, PCB trace size and thickness, airflow and other cooling provision all affect the part temperature. Part temperature should be verified in the end application.


Note 7.: The rated current as listed is either the saturation current or the heating current depending on which value is lower.

### 6. Structure



### 7. Current Characteristic

XRTC404030S100MBCA




### 8. Reliability

Item	Requirements	Test Methods and Remarks
Insulation Resistance	$\geq 100M\Omega$	100 VDC between inductor coil and The middle of the top surface of the body for 60 seconds.
Solderability	90% or more of electrode area shall be coated by new solde.	Dip pads in flux . Solder Composition: Sn/Ag3.0/Cu0.5(Pb-Free). Solder Temperature: $245 \pm 5^\circ\text{C}$ . Immersion Time: $(5 \pm 1)$ s.
Resistance to Soldering Heat	No visible mechanical damage. Inductance change: Within $\pm 10\%$ .	Dip pads in flux. Solder Composition: Sn/Ag3.0/Cu0.5(Pb-Free). Solder Temperature: $260 \pm 5^\circ\text{C}$ . Immersion Time: $10 \pm 1$ sec.
Adhesion of teral electrode	Strong bond between the pad and the core, without come off PCB.	Inductors shall be subjected to $(260 \pm 5)^\circ\text{C}$ for $(20 \pm 5)$ s Soldering in the base whit 0.3mm solder. And then aplombelectrode way plus tax 12 N for $(10 \pm 1)$ seconds.
High temperature	No case deformation or change in appearance. Inductance change: Within $\pm 10\%$	Temperature: $125 \pm 2^\circ\text{C}$ . Time : 1000 hours. Measurement at $24 \pm 4$ hours after test conclusion.
Low temperature	No visible mechanical damage. Inductance change: Within $\pm 10\%$	Temperature: $-55 \pm 2^\circ\text{C}$ . Time : 1000 hours. Measurement at $24 \pm 4$ hours after test conclusion.
Thermal shock	No visible mechanical damage. Inductance change: Within $\pm 10\%$	The test sample shall be placed at $(-55 \pm 3)^\circ\text{C}$ and $(125 \pm 3)^\circ\text{C}$ for $(30 \pm 3)$ , different temperature conversion time is 2~3 utes. The temperature cycle shall be repeated 32 cycles. Placed at room temperature for 2 hours, within $48 \pm 4$ hours of testing.
Temperature characteristic	Inductance change Pc-b,Pc-d: Within $\pm 10\%$	a: $+20^\circ\text{C}$ (30~45) → b: $-40^\circ\text{C}$ (30~45) → c: $+20^\circ\text{C}$ (30~45) → d: $+125^\circ\text{C}$ (30~45) → e: $+20^\circ\text{C}$ (30~45) $P_{c-b} = \frac{L_b - L_c}{L_c} \times 100\%$ ; $P_{c-d} = \frac{L_d - L_c}{L_c} \times 100\%$
Static Humidity	No visible mechanical damage. Inductance change: Within $\pm 10\%$	Inductors shall be subjected to $(95 \pm 3)\%RH$ . at $(60 \pm 2)^\circ\text{C}$ for $(1000 \pm 4)$ h. Placed at room temperature for 2 hours, within 48 hours of testing.
Life	No visible mechanical damage. Inductance change: Within $\pm 10\%$	Inductors shall be store at $(85 \pm 2)^\circ\text{C}$ for $(1000 \pm 4)$ hours with Irms applied. Placed at room temperature for 2 hours, within 48 hours of testing

## 9. Soldering Condition

(This is for recommendation, please customer perform adjustment according to actual application)

Recommend Reflow Soldering Profile : (solder : Sn96.5 / Ag3 / Cu0.5)



Profile Feature	Lead (Pb)-Free solder
Preheat:	
Temperature Min (T <sub>smin</sub> )	150°C
Temperature Max (T <sub>smax</sub> )	200°C
Time (T <sub>smin</sub> to T <sub>smax</sub> ) (t <sub>s</sub> )	60 -120 seconds
Average ramp-up rate: (T <sub>s</sub> max to T <sub>p</sub> )	3°C / second max.
Time maintained above :	
Temperature (T <sub>L</sub> )	217°C
Time (t <sub>L</sub> )	60-150 seconds
Peak Temperature (T <sub>p</sub> )	260°C
Time within $\begin{matrix} +0^{\circ}\text{C} \\ -5 \end{matrix}$ of actual peak Temperature (t <sub>p</sub> ) <sup>2</sup>	10 seconds
Ramp-down Rate	6°C/second max.
Time 25°C to Peak Temperature	8minutes max.


Allowed Re-flow times : 2 times

Remark : To avoid discoloration phenomena of chip on terminal electrodes, please use N<sub>2</sub> Re-flow furnace .

## 10. Packing

### 10I Dimension of plastic taping: (Unit: mm)

The following dimensions are related to the actual fit of the machine, for reference only.




Series	W	A0	B0	D0	D1	E
tolerance	/	/	/	+0.1/-0	±0.20	±0.10
404030	12.0±0.30	4.40±0.10	4.40±0.10	1.5	1.5	1.75

Series	F	K0	P0	P2	P1	T	package quantity
tolerance	±0.10	/	±0.10	±0.10	±0.10	±0.05	
404030	5.5	3.10±0.10	4.0	2.0	8.0	0.35	

### 10II Dimension of Reel : (Unit: mm)

Type	A	B	C
All	±2.0	±2.0	±2.0
All	178	60	13



## 11. Note

- 11I recommend products store in warehouse with temperature between 15 to 35°C under humidity between 25 to 75%RH. Even under storage conditions recommended above, solder ability of products will be degraded stored over 1 year old.
- 11II Cartons must be placed in correct direction which indicated on carton, otherwise the reel or wire will be deformed.
- 11III Storage conditions as below are inappropriate:
  - a. Stored in high electrostatic environment
  - b. Stored in direct sunshine, rain, snow or condensation.
  - c. Exposed to sea wind or corrosive gases, such as Cl<sub>2</sub>, H<sub>2</sub>S, NH<sub>3</sub>, SO<sub>2</sub>, NO<sub>2</sub>, etc.
- 11IV The products are used in circuit board thickness greater than 1.6mm. If customers use less than the thickness of the circuit board that you should confirm with the company, in order to recommend a more suitable product.

## 12. Record

Version	Description	Page	Date	Amended by	Checked by
A0	First version	1~5	Nov.6.2023	Chen.Zhang	Congdian.Lu